



EVO-STIK 528 Contact Adhesive

A GENERAL PURPOSE POLYCHLOROPRENE ADHESIVE

Date: 28 October 2015

Fact Sheet No.: TDS00442

YOUR SMART ADVANTAGES

- High initial grab, with excellent final bond strength
- High shear strength, with good temperature resistance
- Easy application by serrated spreader

USES

EVO-STIK 528 Contact Adhesive is intended for use in interior situations. It may also be used in exterior situations where it can be protected from the weather (sun and rain) e.g. bonding laminates. The new improved (toluene free) formulation has a lower odour and is clearer.

EVO-STIK 528 Contact Adhesive is ready for use and bonds decorative laminates (e.g. Formica), rigid PVC, wood, chipboard, hardboard, cork, leather, some rubber, stone, metal and dense firm fabrics. EVO-STIK 528 Contact Adhesive may also be used to bond insulating fibreboards and acoustic tiles to suspended or vertical surfaces such as flat-surfaced ceilings or walls.

Do not use EVO-STIK 528 Contact Adhesive on polystyrene or on cellulose painted surfaces.

PRODUCT CHARACTERISTICS

Colour	Translucent amber		
Form	Viscous liquid		
Specific Gravity	0.84 approx.		
Composition	Blend of polychloroprene rubber and synthetic resins, in a mixture of petroleum solvents.		
Product Codes	30803761	500ml	x 24
	30803762	1 Litre	x 12

	30813330	2.5 Litre	x 1
	30021180	5 Litre	x 1
Storage/Shelf Life	Store for up to 12 months from date of manufacture when stored in original, unopened packaging under dry conditions within the temperature range of +5°C to +25°C.		
Odour	Sweet hydrocarbon		
TYPICAL PERFORMANCE DATA (Approx.)			
Application Temperature	+5°C to +30°C.		
Service Temperature	-40°C to +65°C.		
Coverage	4 - 6m ² per litre per coat, depending upon the surface type		
Drying Times	10 to 20 minutes Full bond strength after 24 to 48 hours.		
Open Time	Up to 45 minutes		

DIRECTIONS FOR USE

IMPORTANT: Before using EVO-STIK 528 Contact Adhesive refer to the relevant Health & Safety Data Sheet, available at www.bostik.co.uk.

PREPARATION

1. All surfaces to be bonded must be smooth, clean, dry and free from dust and grease.
2. Smooth or polished surfaces must be roughened with a fine abrasive.



FM 01696
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 www.bostik.co.uk

Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.

3. If degreasing is necessary, a detergent/water treatment should first be considered. If this is inappropriate, a suitable solvent such as EVO-STIK Adhesive Cleaner may be used. It is advisable to check the effects of degreasing solvents on plastics, rubber materials and painted surfaces before carrying out the operation. All traces of cleaning solvents must be allowed to evaporate before application of the adhesive.

APPLICATION

4. Apply an even ribbed coating of adhesive to both surfaces to be bonded, using a trowel or spreader with a serrated edge and taking care that its serrations are neither worn nor filled with dried adhesive.
5. To ensure the correct coverage is obtained use the spreader at such an angle as to give good rib formation after drying.
6. Keep the surfaces separated until both the adhesive films are touch dry.
7. When working at high relative humidity, condensation of moisture on the adhesive film may take place, recognisable by the appearance of a white 'bloom' on the surface. This can be detrimental and work should not continue until conditions have improved by raising the temperature and/or drying the atmosphere. This depends on such variables as spreading thickness, surface porosity, and ambient temperature and humidity.
8. Typical touch dry times are 10 to 15 minutes for porous substrates and 10 to 20 minutes for non-porous substrates.
9. Normally assembly should not be delayed for more than 45 minutes after application.
10. Bring the two coated and touch dry surfaces into contact and press together over the whole bond area.
11. Hand pressure is normally sufficient but a suitable press or a rubber hand roller may often be used with advantage.
12. Sustained pressure is necessary.

CLEANING

13. Remove as much of the adhesive as possible by mechanical means.
14. Adhesive can be removed using a cloth dampened with acetone or EVO-STIK Adhesive Cleaner.
15. Always check if the cleaning solvent might damage a nearby surface by testing.

PRECAUTIONS IN USE

EVO-STIK 528 Contact Adhesive is unsuitable for use with expanded polystyrene, or plasticized PVC (vinyl).

Do not use on or near bituminous surfaces.

EVO-STIK 528 Contact Adhesive will not bond polyolefins such as polyethylene and polypropylene.

It is not suitable for use where only point contact exists between the surfaces to be bonded.

Bringing the surfaces together before they are touch dry will result in solvent being trapped, this will adversely affect the final bond and may give rise to blistering problems, particularly if the adhesive has not been evenly spread.

EVO-STIK 528 Contact Adhesive forms a bond as soon as the two surfaces touch. It is therefore essential to avoid contact before the parts are in alignment, such as by insertion of pins along one edge of one surface, against which the other surface can be located.

The initial bond strength allows immediate handling of the assembly but maximum bond strength is reached after approx. 24 to 48 hours at normal temperatures.

For any application not covered please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.co.uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data Sheet for EVO-STIK 528 Contact Adhesive, available at www.bostik.co.uk.

BOSTIK HOTLINE

Smart help +44 (0) 1785 272625



FM 01696
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 www.bostik.co.uk

Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 0844 371 1192	Fax: 01785 241818	customer.service@bostik.com
Technical Advice	Tel: 0844 371 1197	Fax: 01785 272867	technical.service@bostik.com
Technical Data & COSHH (MSDS) Data Sheets	Tel: 01785 272625	Fax: 01785 212962	stafford.gatehouse@bostik.com



FM 01696
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 www.bostik.co.uk
Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.